

## PRODUCT DATA SHEET

# Purolite® A109

Polystyrenic Macroporous, Weak  
Base Anion Resin, Free Base form

## PRINCIPAL APPLICATIONS

- Demineralization
- Natural-Organic-Matter-(NOM)-Removal

## ADVANTAGES

- High porosity
- Excellent resistance to osmotic shock
- Excellent chemical and thermal stability

## REGULATORY APPROVALS

- IFANCA Halal Certified

## TYPICAL PACKAGING

- 1 ft³ Sack
- 25 L Sack
- 5 ft³ Drum (Fiber)
- 1 m³ Supersack
- 42 ft³ Supersack
- Bulk Tanker (NA only)

## TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Primary Amine
Ionic Form	FB
Total Capacity (min.)	1 eq/L (21.8 Kgr/ft³) (FB form)
SBC	0 - 5 %
Moisture Retention	58 - 65 % (FB form)
Particle Size Range	425 - 1000 µm
< 425 µm (max.)	2 %
Uniformity Coefficient (max.)	1.6
Reversible Swelling, FB → Cl⁻ (max.)	25 %
Specific Gravity	1.05
Shipping Weight (approx.)	660 - 685 g/L (41.2 - 42.8 lb/ft³)
Temperature Limit	100 °C (212.0 °F) (Cl⁻ form)
Temperature Limit	60 °C (140.0 °F) (FB form)

Purolite, an Ecolab company, is a



## We're ready to solve your process challenges.

For further information on Purolite products and services, visit [www.purolite.com](http://www.purolite.com) or contact us at the addresses below.

The statements, technical information and recommendations contained herein are believed to be accurate as of the date hereof. Since the conditions and methods of use of the product and of the information referred to herein are beyond our control, Purolite expressly disclaims any and all liability as to any results obtained or arising from any use of the product or reliance on such information; NO WARRANTY OF FITNESS FOR ANY PARTICULAR PURPOSE, WARRANTY OF MERCHANTABILITY OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, IS MADE CONCERNING THE GOODS DESCRIBED OR THE INFORMATION PROVIDED HEREIN. The information provided herein relates only to the specific product designated and may not be applicable when such product is used in combination with other materials or in any process. Nothing contained herein constitutes a license to practice under any patent and it should not be construed as an inducement to infringe any patent and the user is advised to take appropriate steps to be sure that any proposed use of the product will not result in patent infringement.